

## PATENT ABSTRACTS OF JAPAN

(11)Publication number : 05-320519  
 (43)Date of publication of application : 03.12.1993

(51)Int.Cl.

C08L 83/10  
 C08K 3/22  
 C08L 69/00

(21)Application number : 04-127047

(71)Applicant : IDEMITSU PETROCHEM CO LTD

(22)Date of filing : 20.05.1992



(72)Inventor : UMEDA TAKASHI  
 SUGITA YASUHISA  
 OKAMOTO MASAYA

## (54) POLYCARBONATE RESIN COMPOSITION

## (57)Abstract:

PURPOSE: To obtain a resin composition, comprising a polycarbonate-polyorganosiloxane copolymer, a polycarbonate resin and a white pigment in a specific proportion, excellent in impact resistance, rigidity, optical characteristics, etc., and capable of reducing the weight.

CONSTITUTION: The objective composition is obtained by blending 100 pts.wt. total amount of (A) 5-100wt.% polycarbonatepolyorganosiloxane copolymer [preferably composed of a polycarbonate part expressed by formula I (R1 and R2 are H, halogen or 1-8C alkyl; (m) and (n) are 1-4; Z is 1-8C alkylene, 2-8C alkylidene, 5-15C cycloalkylene, SO<sub>2</sub>, SO, S, etc.) and a polyorganosiloxane part expressed by formula II (R3 to R5 are H, 1-6C alkyl or phenyl; (p) and (q) are 0 or ≥1) and (B) 95-0wt.% polycarbonate resin with (C) 1-30 pts.wt. white pigment. The ratio of the polyorganosiloxane part in the component (A) is 0.1-40wt.% based on the total amount of the components (A) and (B).



## LEGAL STATUS

[Date of request for examination] 22.04.1999  
 [Date of sending the examiner's decision of rejection] 09.07.2002  
 [Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]  
 [Date of final disposal for application]  
 [Patent number] 3390465  
 [Date of registration] 17.01.2003  
 [Number of appeal against examiner's decision of rejection] 2002-15023  
 [Date of requesting appeal against examiner's decision of rejection] 08.08.2002  
 [Date of extinction of right]

Copyright (C), 1998,2003 Japan Patent Office